

EverGuard™ TPO 60mil Membrane

Specification Sheet



*Quality You Can Trust Since 1886...
From North America's Largest Roofing Manufacturer™*

Product Data Sheet EverGuard® TPO 60 mil Membrane

Title 24 *
Compliant



Description

GAF EverGuard® TPO 60 mil thermoplastic polyolefin single-ply membrane systems have been engineered to provide superior long-term performance and enhanced durability. Strong, flexible EverGuard TPO 60 mil membrane is suitable for use in all types of single-ply systems: Mechanically Attached, Fully Adhered, and Ballast Applied

Compared to other heavy-duty single-ply EPDM, PVC and TPO membranes, GAF EverGuard TPO 60 mil roofing membrane provides the benefits of all three materials in a single membrane: low installed cost, heat welded seams, white reflective color, and no liquid plasticizers.

Applicable Standards

UL Listed, FM Approved, Dade County Product Approval, Florida Building Code Approved, CRRC Listed, Title 24 Compliant, ENERGY STAR® Listed, ASTM D6878.

Physical Properties	ASTM Test Method	ASTM 6878 Minimum	EverGuard Typical Test Data
1. Certain data is provided in MD (machine direction) x CMD (cross machine direction) format. 2. Data is based upon typical product performance, and is subject to normal manufacturing tolerance and variance			
Nominal Thickness	ASTM D-751	0.039" (min.)	0.060"
Breaking Strength	ASTM D-751 Grab Method	220 lbf/in.	330 lbf x 310 lbf
Factory Seam Strength	ASTM D-751	66 lbf	120 lbf (membrane failure)
Elongation at Break	ASTM D-751	15%	30%
Heat Aging	ASTM D-573	90% Retention of Breaking Strength and Elongation at Break	100%
Tear Strength	ASTM D-751 8" x 8" Sample	55 lbf	70 lbf x 150 lbf
Puncture Resistance	FTM 101C Method 2031	Not Established	380 lbs.
Cold Brittleness	ASTM D-2137	-40 C	-40 C
Permeance	ASTM E-96	Not Established	0.01 Perms
Dimensional Change	ASTM D-1204 @ 158 F, 6 hrs.	+/- 1%	0.4%
Water Absorption	ASTM D-471 @ 158 F, 1 week	+/- 3.0% (top coating only)	0.7%
Hydrostatic Resistance	ASTM D-751 Method D	Not Established	430 psi
Ozone Resistance	ASTM D-1149	Pass No visible deterioration @ 7 x magnification	No visible deterioration @ 7 x magnification
Reflectivity (white)	ASTM C1549	N/A	0.76
Emissivity (white)	ASTM C1371	N/A	0.90

Product Data

Roll Size	Note: Product sizes, dimensions, and widths are nominal values and are subject to normal manufacturing/packaging tolerance and variation				
	Colors	Full Roll Size	Full Roll Weight	Half Roll Size	Half Roll Weight
	White, Tan, Gray, Regal Red, Regal Blue, Hartford Green	10' x 100' (1,000 sq.ft.)	322 lbs.	5' x 100' (500 sq.ft.)	162 lbs.
Note: Membrane rolls shipped horizontally on pallets.					
Storage	Store rolls on their sides on pallets or shelving in a dry area				
Safety Warning	Membrane rolls are heavy. Position and install by at least two people.				

* White Membrane Only